

GlossCoat™ 100 BL

BRAND FAMILY OVERVIEW GlossCoat™ postprint OPVs reduce the porosity of corrugated and solid fiber while adding luster. They protect printing and improve sheet feeder/case erector performance.

USAGE This fully formulated, flexo applicable nonskid coating is designed for kraft, mottled and bleached substrates.

DESCRIPTION Water based, nonskid post print varnish for porous substrates

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

Market	Properties Imparted
Industrial	skid resistance

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Off-white liquid
Solids Type:	Acrylic
EZ Cup Viscosity (sec) :	20 - 28
Cup Number:	2
pH:	8.7 - 9.7

SITE OF MANUFACTURE (and PRODUCT CODE) USA (GC100BL), Singapore (GC100BL.S)

APPLICATION DATA GlossCoat™ 100BL should be applied by flexo.

STORAGE Keep container tightly closed. Keep containers tightly closed in a dry, cool and well-ventilated place. Keep from freezing.

HANDLING Ensure adequate ventilation. Handle in accordance with good industrial hygiene and safety practice. Use personal protective equipment as required.

Revised 12 May 2017

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

GlossCoat™ 100 BL

Americas

Michelman Inc.
Tel: +1 513 793 7766
Fax: +1 513 793 2504

Luxembourg

Michelman International SARL
Tel: +352 26 39 44 1
Fax: +352 26 39 44 80

Singapore

Michelman Asia-Pacific Pte. Ltd.
Tel: +65 6861 2822
Fax: +65 6861 2262

China

Michelman New Material
(Shanghai) Co., Ltd.
Tel: +86 21 3810 3800
Fax: +86 21 3810 3811

India

Michelman Private Limited
Tel: +91 22 6221 3800
Fax: +91 22 6221 3801/02

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2025 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.